




SINCE 1968

TOUGH
TO BEAT

Style 39



Product Description

Selected Grade of Quality Asbestos Fibres & Fillers bonded with special rubber compound for meeting with the exacting requirements of modern industry.



Appropriate/Suitable Media

For Transmission and Hydraulic Fluids, Alkalies, Anti Freeze, Refrigerating Oils & Solvents including Steam. (Medium Service Condition)



AVAILABLE SIZES

Standard Sheet Size (mm)	1600/1500 x 1500 1600/1500 x 2000 1600/1500 x 3000 1600/1500 x 6000 1525 x 1650 1525 x 5000 2000 x 6000 2000 x 2000 3000 x 3000 1000 x 1000 2000 x 3000
Thickness (mm)	0.40 to 6.00 for Non Metallic & 0.50 to 6.00 for Metallic
Thickness Tolerances (mm)	Upto & including 0.50 = ± 0.05 Over 0.50, Upto & including 1.00 = ± 0.10 Over 1.00 Upto & including 2.00 = ± 0.15 Over 2.00 Upto & including 3.00 = ± 0.20 Over 3.00 Upto & including 4.00 = ± 0.30 Over 4.00 = ± 0.40



TECHNICAL INFORMATION

Compliance	IS 2712 Grade O/2	
Category	Asbestos	
Line Callout Number	ASTMF104F112999A9B9E99M9T3	
Colour	Non Metallic	Red-Grey/Black Graphited
	Metallic	With special metallic reinforcement To enhance strength & suitability



Suitable Industries/ Properties

Suitable for low to medium Stress Conditions. For Motor oil transmission, hydraulic fluids, low temperature oils, Antifreeze, Refrigerating Oil.


Parameters	Standard	Unit	Value	
			Non Metallic	Metallic
Density	IS 2712	g/cc	1.80-2.20	1.85-2.40
Tensile Strength	IS 2712	Kg/cm ²	≥ 150	≥ 160
Compressibility	IS 2712	%	8-12	8-12
Recovery	IS 2712	%	≥ 45	≥ 45
Ignition Loss	IS 2712	%	≤ 20	≤ 20
Stress Relaxation (Residual Stress)	IS 2712	N/mm ²	20	21
Flexibility @RT (Cracking, delamination or distress)	IS 2712	—	OK	OK
Oil Absorption 5 H @ 150°C (Thickness/Mass)	IS 2712	%	$\leq 15/ \leq 15$	$\leq 15/ \leq 15$
Fuel B Absorption 22 H @ RT (Thickness/Mass)	IS 2712	%	$\leq 15/ \leq 16$	$\leq 15/ \leq 16$
Water Absorption 5 H @ 100°C (Thickness/Mass)	IS 2712	%	≤ 8	≤ 8
Recommended Maximum Temperature	--	°C	450	480
Recommended Maximum Pressure	—	Kg/cm ²	85	100

Note:

- All metallic insert sheets are available with graphite finish.

TYPICAL VALUES FOR A THICKNESS OF 1.60 mm

Gasket Factors	Thickness (mm)	"M" Factor	"Y" Stress (Psi)
	0.80	3.50	6500
	1.60	2.75	3700
	3.20	2.00	1600



PERFORMANCE CHART & RECOMMENDATION

Maximum Values of Temperature and Pressure should not be used simultaneously, they are given only as guidance. Maximum Temperature and Pressure depends not only on the type of gasket material but also on the application conditions such as thickness of material, nature of service medium, type of flange, surface stress etc.

- XA** General suitability using common installation practices under conditions of chemical compatibility
- XB** Maximum performance is ensured through appropriate measures for joint designs and gasket installations. Consultation is recommended.
- XC** Limited application area. Technical consultation is mandatory
- XD** Area not recommended

For detailed selection criteria, technical information, installation guideline and a complete listing of local sales offices please visit www.spitmaan.com

CHAMPION JOINTINGS PVT LTD.

15, Parsi Panchayat Road, Andheri East, Mumbai 400069 INDIA.

+91 22 40888000

CJPL@spitmaan.com

www.spitmaan.com

The information in the catalogue is intended for use by persons possessing technical skills at their own discretion and risk. The company assumes no obligation or liability in connection with its use. All data in this catalogue is based on practical experience and is intended for information & guidelines.